

## **PRODUCT INSTRUCTIONS: FIXING AGENT**

After completing the dyeing process and rinsing in cold water, squeeze material to remove excess liquid. Prepare soak bath with warm water sufficient to cover material. Add 10ml Tintex Fixing Agent per litre of water and swirl to mix. Add material, move slowly in soak bath to absorb dye fix evenly. Allow to stand 10-15 minutes. Remove material and allow to drip dry. Press material with hot dry iron to cure dye fix.